

### AFC ANTI-FRICTION COMPOSITION EP GREASE

Whitmore's Anti-Friction Composition is a series of high performance sodium-based greases that are designed for use in slow-moving applications as encountered in industries such as mining, primary metals, cement, and aggregate production.

The AFC greases are fibrous, stringy, and adhesive. Excess grease will form a collar or lip around the seal. This helps in keeping out dust and contaminants.

AFC greases can be used in any bearing or other application where conventional grease is appropriate for lubrication; however they are particularly effective on plain bushings, whether Babbitt, bronze, or leaded steel.

The natural adhesiveness of Whitmore's AFC greases provides excellent film forming characteristics and outstanding resistance to pound out.

AFC greases meet the Extraction Procedure Toxicity guidelines established by the Environmental Protection Agency, which excludes them from the stringent storage and disposal requirements of the EPA Hazardous Waste law.

Maximum DN factor for  
 AFC No. 5 (NLGI grade 2): 180,000  
 Maximum continuous temperature: 200°F (93°C)  
 Maximum occasional temperature: 250°F (121°C)  
 Appearance: Black, stringy, adhesive

To calculate the DN factor of a bearing, use the following:  
 DN factor for a bearing =  $dm \times rpm$   
 Where  $dm =$  (bearing inside diameter in millimeters + bearing outside diameter) divided by 2

#### BENEFITS:

- EXTREME LOAD-CARRYING ABILITY - protects from seizure during shock loads.
- REDUCES FRICTION AND WEAR - fortified with EP additives to provide longer equipment life.
- ENERGY EFFICIENT - lowers friction drag for reduced amperage draw.
- PROTECTS UNDER ADVERSE CONDITIONS - tough adhesive and cohesive thickener.
- SEALS OUT CONTAMINANTS – forms a fibrous seal to protect moving parts from dust.

#### APPLICATIONS:

Choose AFC greases where lubricated components are subjected to high load, slow speed, and contamination.

Recommended for conveyor bearings, calendars, rubber mill bearings, and motor bearings in dusty conditions. Use in bearings in the primary metals or mining industries that operate under high load at slow speeds, i.e., crushers, shaker screens, pelletizers, and centrifuges.

AFC greases are not suitable for use under water.

ASTM #		TYPICAL CHARACTERISTICS		
		No. 5	No. 3	No. 3WW
D-217	<b>Cone Penetration</b>	275-305	320-350	375-405
D-566	<b>Dropping Point, °F (°C)</b>	350 (177)	330 (166)	310 (154)
D-445	<b>Kinematic Viscosity</b>			
	cSt @ 40°C	185	185	87
	cSt @ 100°C	15.4	15.4	9.5
D-2161	<b>Saybolt Viscosity</b>			
	SUS @ 100°F	1,000	1,000	460
	SUS @ 210°F	80	80	58
Gardner Method	<b>Density, lb/gal @ 60°F (15.5°C)</b>	7.70	7.74	7.72
D-2596	<b>Specific Gravity, g/cc @ 60°F (15.5°C)</b>	0.925	0.929	0.927
	<b>Four Ball EP</b>			
	Weld Point, kg	315	315	315
	Load Wear Index	50	50	50
	<b>Thickener Type</b>	Sodium	Sodium	Sodium
OEM Standard	<b>Low Temperature Pumpability</b>			
	Lincoln Ventmeter @ 400 psi, °F (°C)	35 (2)	5 (-15)	-10 (-23)

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

#### PACKAGING

Shuttle Tanks	Drums	Kegs	Pails
---------------	-------	------	-------

#### THE WHITMORE MANUFACTURING COMPANY

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108

An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • <http://www.whitmores.com>

Performance Under Pressure Since 1893

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.