



# TECHNICAL DATA SHEET

## COMPASS™ EP HEAVY DUTY LUBRICATING GREASE

The primary features of this heavy-duty grease are tolerance for water and the ability to withstand heavy loads.

Compass™ EP is a lithium grease, fortified with synthetic polymers that cause the grease to cling to metal and repel water, even at high pressure.

When water does eventually get mixed into the body of the grease, the impact is less than with conventional grease. Compass™ EP contains additives that counteract the negative impact of water ingress. During standardized laboratory testing, water was mixed for 5,000 strokes; the degree of softening was then measured. There was no measurable effect on the consistency of the grease. Under this test, many greases become soft to the point of flowing.

The ability of Compass™ EP to withstand extreme pressure is evidenced by the high weld point (500 kilograms) on the Four Ball machine. End users consistently report that Compass™ EP performs under load as well as greases that cost substantially more.

### BENEFITS:

- RESISTS WATER – keeps a protective film on metal.
- STABLE – retains its body under high load or when water enters.
- WEAR PROTECTION – contains molybdenum disulfide for protection under high load.
- PUMPABLE – can be used in automatic systems at low temperatures.

### APPLICATIONS:

Recommended for slow and medium speed industrial bearings, especially those that are exposed to high load and/or water. Use in steel mills and other primary metal processing, pulp and paper operations, waste water treatment facilities, cement mills, rubber and plastics, marine applications, mining, logging, construction, etc.

ASTM #		TYPICAL CHARACTERISTICS
	<b>Grade</b>	EP 2
D-217	<b>Cone Penetration (Worked)</b>	265-295
D-2265	<b>Dropping Point, °F (°C)</b>	396 (202)
D-445	<b>Kinematic Viscosity (Base Oil w/Polymer)</b>	
	cSt @ 40°C	925
	cSt @ 100°C	36
Gardner Method	<b>Density, lb/gal @ 60°F (15.5°C)</b>	8.28
D-2596	<b>Specific Gravity, g/cc @ 60°F (15.5°C)</b>	0.9942
	<b>Four Ball EP</b>	
	Weld Point, kg	500
D-2266	<b>Four Ball Wear</b>	
	Scar Width, mm	0.56
D-4049	<b>Water Spray Off, % Loss</b>	15
D-1264	<b>Water Washout, % Loss</b>	<5
D-1743	<b>Rust Test</b>	Pass
D-4048	<b>Copper Strip Corrosion for Greases</b>	1B
(Modified)	212°F (100°C) @ 3 hrs	
OEM	<b>Low Temperature Pumpability</b>	
Standard	Lincoln Ventmeter @ 400 psi, °F (°C)	22 (-6)
	<b>Thickener Type</b>	Lithium

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

### PACKAGING

Shuttle Tanks	Nonreturnable Totes	Drums	Kegs	Pails
---------------	---------------------	-------	------	-------

### THE WHITMORE MANUFACTURING COMPANY

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108  
An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • <http://www.whitmores.com>  
Performance Under Pressure Since 1893

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.