



# TECHNICAL DATA SHEET

## HYPERION™ HYDRAULIC/TURBINE/COMPRESSOR OILS

Whitmore's Hyperion™ oils bring together several developments in both base oil and additive technology to create a true multifunctional product. Hyperion™ oils meet the needs of today's high precision hydraulic systems, turbines, and air compressors.

Hyperion™ has been formulated using the highest quality severely hydroprocessed paraffinic oils. Laboratory tests and field experience have clearly demonstrated the positive impact of these base oils on finished product properties and performance.

In laboratory tests, Hyperion™ severely hydroprocessed base oil shows a major reduction in evaporation loss. Oxidation stability exceeds that of conventional base oils by 60-100%. These performance improvements translate into reduced carbon and varnish deposits. The end result is longer oil and component life.

Whitmore uses an ashless (zinc-free) additive system that has been specifically tailored to these base oils. This further enhances the longevity and high temperature performance of the Hyperion™ series. An extension in oil life of 50% can be expected. (The use of oil analysis to determine ideal change frequency is recommended.)

Use Hyperion™ in rotary screw compressors where the discharge temperature ranges up to 190°F (88°C).

### BENEFITS:

- **LONG LIFE** - 50% longer oil life. Further extension is possible depending on operating temperature and maintenance practices, such as filtration.
- **REDUCED DEPOSITS** - less carbon and varnish means reduced stress and wear on components.
- **ANTIWEAR PROTECTION** - offers wear protection without the surface deposits that are created by zinc-based additive systems. These deposits can cause stickiness in high-precision spool valves.
- **RESISTS FOAMING** - low foaming tendency. Entrained air is readily released.

### APPLICATIONS:

Hyperion™ oils are suitable for use in hydraulic systems, turbines and the majority of flooded screw, flooded rotary vane, and reciprocating air compressors. They are also suitable for use on conveyor chains operating at temperatures up to 200°F (93°C). Viscosity grade ISO 32 is recommended for use in compressed air systems for lubrication of air operated tools.

Meets the following OEM requirements:

Vickers	1-286-S, M-2950-S
Denison	HF-1, HF-2, HF-0
U.S. Steel	127, 136
Cincinnati Milacron	P-68, P-69, P-70
General Motors	LH-04-1, LH-06-01, LH-15-1

ASTM #	ISO Grade	32	46	68	100	150	220	320	460
<b>D-445</b>	<b>Kinematic Viscosity</b>								
	cSt @ 40°C	31	43	64	92	146	220	307	467
	cSt @ 100°C	5	7	9	11	14	19	24	31
<b>D-2270</b>	<b>Viscosity Index</b>	99	102	103	96	95	97	95	94
<b>D-97</b>	<b>Pour Point, °F (°C)</b>	-25 (-32)	-25 (-32)	-25 (-32)	-15 (-26)	-15 (-26)	0 (-18)	10 (-12)	0 (-18)
<b>Gardner Method</b>	<b>Density, lb/gal @ 60°F (15.5°C)</b>	7.19	7.21	7.26	7.30	7.36	7.38	7.40	7.43
	<b>Specific Gravity, g/cc @ 60°F (15.5°C)</b>	0.861	0.863	0.869	0.874	0.881	0.883	0.885	0.889
<b>D-92</b>	<b>Flash Point, °F</b>	400	410	425	440	485	525	530	535
	(°C)	(204)	(210)	(218)	(227)	(252)	(274)	(277)	(279)
<b>D-4172</b>	<b>Four Ball Wear</b>								
	Scar Width, mm @ 40 kg	0.40	0.40	0.40	0.40	0.40	0.40	0.40	0.40
<b>Modified</b>	<b>Four Ball Wear, Scar Width mm</b>								
	60 min, 400 N, 1,420 rpm	0.38	0.38	0.38	0.38	0.38	0.38	0.38	0.38
<b>D-665</b>	<b>Rust Test</b>	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass
<b>D-2272</b>	<b>Oxidation Stability, rotary bomb hrs @ 302°F</b>	26	27	28	30	22	19	15	NA
<b>D-189</b>	<b>Conradson Carbon Residue, % Carbon</b>	0.04	0.05	0.05	0.06	0.06	0.14	0.18	NA
<b>D-943</b>	<b>Oxidation Stability, hrs</b>	15,000	15,000	15,000	15,000	10,000	10,000	7,000	7,000
	<b>FZG Stages Passed</b>	>12	>12	>12	>12	>12	>12	>12	>12

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

### PACKAGING

Drums	Kegs	Pails
-------	------	-------

### THE WHITMORE MANUFACTURING COMPANY

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108

An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • <http://www.whitmores.com>

**LIMITED WARRANTY:** The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.