



TECHNICAL DATA SHEET

MOLY EP ANTI-SEIZE AND GASKET COMPOUND

Whitmore's Moly EP Anti-Seize is a premium formulation with a variety of applications over a wide temperature range. Its homogeneous composition offers maximum protection against seizure and heat-freeze, eases assembling and dismantling, and saves man-hours. It assures protection against rust, oxidation and corrosion. It will not harden, evaporate, or settle out; and it requires no thinning.

Moly EP contains carefully balanced proportions of molybdenum disulfide (MoS₂), graphite, and low friction fillers in an aluminum complex base grease that is fortified with effective rust and corrosion inhibitors. Each principal anti-seize, low-friction ingredient has important properties and characteristics.

Molybdenum disulfide (MoS₂) has an affinity for ferrous metals, bonds itself to steel working surfaces and offers protection from frictional wear and fret corrosion while sustaining lubrication. Graphite provides Extreme Pressure characteristics.

The aluminum complex base grease in Moly EP contains a patented, extreme-pressure additive. This package increases performance because it maintains the proper dispersion and suspension of solid ingredients. It flows evenly over surfaces and into thread courses. It will not drip, assuring that the surface receives maximum protection.

BENEFITS:

- LEAD-FREE
- PROTECTS AGAINST - seizure, heat-freeze, galling, rust, and corrosion.
- LOWERS FRICTION - reduces wrench torque.
- PROVIDES - easy makeup and breakout.
- REDUCES - maintenance costs.
- NOT AFFECTED - by vibration, expansion, or contraction.
- WILL NOT - run, drip, or settle out.

APPLICATIONS:

Use Moly EP:

Tubular Threads	Flange Faces
Gaskets	Keys
Keyways	Slides
Guides	Fittings

Particularly suitable for steel and aluminum. Moly EP works equally well on alloys, stainless steel, cast iron, titanium, plastic, copper, brass, packing, and gasket materials.

NOTE: Not for use on oxygen or LPG lines. Not suitable for stainless steel at temperatures above 550°F (288°C).

ASTM #		TYPICAL CHARACTERISTICS
	NLGI Grade	1
D-217	Cone Penetration (Worked)	310
D-2265	Dropping Point, °F (°C)	500 (260)
Gardner Method	Density, lb/gal @ 60°F (15.5°C) Specific Gravity, g/cc @ 60°F (15.5°C)	9.45 1.134
D-2596	Four Ball EP Weld Point, kg Load Wear Index	500 109
D-4049	Water Spray-Off, % Loss	<12
D-4048 (Modified)	Copper Strip Corrosion for Greases 212°F (100°C) @ 3 hrs	1A
	Thickener Type	Aluminum Complex
B-117	Salt Fog Resistance 20% NaCl @ 100°F (38°C), hr	>200
	Coefficient of Friction on Stainless Steel	0.09
	Service Rating, °F (°C)	-65 (-54) to 1050 (566)
	Color	Dark Gray

The above are average values. A single test result may vary slightly without affecting performance.

PACKAGING

Brush Top Cans 12 – 1 lb cans	Brush Top Cans 12 – 2 lb cans
----------------------------------	----------------------------------

THE WHITMORE MANUFACTURING COMPANY

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108
An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • <http://www.whitmores.com>

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.