

## CALIBER™ 5M EXTREME PRESSURE GREASE with 5% MoS<sub>2</sub>

Whitmore's Caliber™ 5M is a series of extreme pressure lithium complex greases that contain molybdenum. The series is designed primarily for use in draglines, shovels, drills, earthmoving equipment and other heavy-duty rolling stock applications.

Caliber™ 5M contains 5% MoS<sub>2</sub> (molybdenum disulfide) has the extreme pressure capability to prevent wear in very heavily loaded bushings and bearings.

All grades are also available with 3% MoS<sub>2</sub> (Caliber™ 3M).

Note: For operations in extreme cold see data sheet for Caliber™ 3M. See especially the Sub-Zero grade.

### BENEFITS:

- **WATER-RESISTANT** - excellent resistance to washing out of bearings.
- **EXTREME PRESSURE** - protects against shock loads and scuffing of metal surfaces. Reduces parts replacement and downtime.
- **SEALS OUT DIRT AND CONTAMINANTS** - forms a protective barrier to reduce wear and extend lubricant life.
- **VERSATILE FORMULATION** - ideal for a wide range of equipment, including process machinery and industrial applications.

### APPLICATIONS:

Whitmore's Caliber™ 5M is designed to lubricate the components of mining machines, earthmoving equipment and rolling stock. It is recommended for wheel bearings, slewing bearings, vehicle chassis points and U-joints, as well as pivot points and bucket pins on earthmoving equipment.

ASTM #	Grade	TYPICAL CHARACTERISTICS			
		EP 0	EP 1	EP 1.5	EP 2
D-217	Cone Penetration (Worked)	355-385	310-340	285-315	265-295
D-2265	Dropping Point, °F (°C)	450 (232)	472 (244)	475 (245)	507 (264)
D-445	Kinematic Viscosity (Base Oil + Polymer) cSt @ 40°C cSt @ 100°C	130 13	220 19	280 20	300 21
Gardner Method	Density, lb/gal @ 60°F (15.5°C)	7.59	7.59	7.56	7.53
D-2509	Timken OK Load, lb	65	65	65	65
D-2596	Four Ball EP Weld Point, kg (Minimum)	620	620	620	620
D-2266	Four Ball Wear, Scar Width, mm	0.40	0.40	0.40	0.40
D-1264	Water Washout, % Loss	Not Tested	Not Tested	5	<3.5
D-1743	Rust Test	1,1,1 (Pass)	1,1,1 (Pass)	1,1,1 (Pass)	1,1,1 (Pass)
D-4048 (Modified)	Copper Strip Corrosion for Greases 212°F (100°C) @ 3 hrs	1B	1B	2B	2B
OEM Standard	Low Temperature Pumpability Lincoln Ventmeter @ 400 psi, °F (°C)	-15 (-26)	8 (-13)	18 (-7)	23 (-5)
	Ambient temperature range, °F °C	-20 to 50 -30 to 10	-5 to 80 -21 to 27	5 to 90 -15 to 32	10 to 200 -12 to 93

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

### PACKAGING

Shuttle Tanks	Nonreturnable Totes	Drums	Pails
---------------	---------------------	-------	-------

For warranty information, scan the QR code.  
You can also email us at [sales@whitmores.com](mailto:sales@whitmores.com)  
Or write to the Sales Department at the address below.

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318  
An ISO 9001 and ISO 14001 registered company • [www.whitmores.com](http://www.whitmores.com)

